

## **Description**

Enviro-Matt<sup>TM</sup> Bonded Fiber Matrix (BFM) is 100% biodegradable, made in the United States and composed of 100% recycled, thermally refined (within a pressurized vessel) virgin wood fibers and wetting agents (including high-viscosity colloidal polysaccharides and cross-linked biopolymers). The BFM is phytosanitized, free from plastic netting, and when cured forms an intimate bond with the soil surface to create a continuous, porous, absorbent and flexible erosion resistant blanket that allows for rapid germination and accelerated plant growth. The BFM may require a 4-8 hour curing period to achieve maximum performance.

# **Recommended Applications**

- Erosion control for slopes ranging from mild to steep (≤1H:1V)
- · Rough graded slopes
- · Equivalent performance as rolled erosion control blankets with plastic nettings
- Enhancement of vegetation establishment

### **Technical Data**

Physical Properties*	Test Method	Units	Tested Value
Mass/Unit Area	ASTM D6566 <sup>1</sup>	g/m² (oz/yd²)	≥ 390 (11.6)
Thickness	ASTM D6525 <sup>1</sup>	mm (in)	≥ 3 (0.12)
Ground Cover	ASTM D6567 <sup>1</sup>	%	≥ 97
Water Holding Capacity	ASTM D7367	%	≥ 1,400
Material Color	Observed	n/a	Green
Performance Properties*	Test Method	Units	Tested Value
Cover Factor <sup>2</sup>	Large Scale <sup>4</sup>	n/a	≤ 0.05
Percent Effectiveness <sup>3</sup>	Large Scale⁴	%	≥ 95
Cure Time	Observed	hours	4 - 8
Vegetation Establishment	ASTM D7322 <sup>1</sup>	%	≥ 600
Functional Longevity <sup>5</sup>	ASTM D5338	Months	≤ 12
Environmental Properties*	Test Method	Units	Tested Value
Ecotoxicity	EPA 2021.0	%	48-hr LC <sub>50</sub> > 100%
Biodegradability	ASTM D5338	n/a	Yes
Product Composition			Typical Value
Thermally Processed Wood Fiber <sup>6</sup> (within a pressurized vessel)			90%
Wetting Agents - including high-viscosity colloidal polysaccharides and cross-linked biopolymers			10%

\*When uniformly applied at a rate of 3500 pounds per acre (3900 kilograms/hectare) under laboratory conditions. 1. ASTM test methods developed for Rolled Erosion Control Products that have been modified to accommodate Hydraulic Erosion Control Products. 2. Cover Factor is calculated as soil loss ratio of treated surface versus an untreated control surface. 3. % Effectiveness = One minus Cover Factor multiplied by 100%. 4. Large scale testing conducted at Utah Water Research Laboratory. For specific testing information please contact a Profile technical service representative at 800-508-8861 or +1-847-215-1144. 5. Functional Longevity is the estimated time period, based upon field observations, that a material can be anticipated to provide erosion control and agronomic benefits as influenced by composition, as well as site-specific conditions, including; but not limited to – temperature, moisture, light conditions, soils, biological activity, vegetative establishment and other environmental factors. 6. Heated to a temperature greater than 380 degrees Fahrenheit (193 degrees Celsius) for 5 minutes at a pressure greater than 50 psi (345 kPa) in order to be Thermally Refined \*\*/Processed and to achieve phytosanitization.

## **Packaging Data**

Properties	Test Method	Units	Nominal Value
Bag Weight	Scale	kg (lb)	22.7 (50)
Bags per Pallet	Observed	#	40

UV and weather-resistant plastic bags. Pallets are weather-proof stretch wrapped with UV resistant pallet cover.

#### **Profile Products**

750 Lake Cook Road, Ste. 440 Buffalo Grove, IL 60089 800-508-868 or +1-847-215-1144 www.profileproducts.com